

VERSION WITH MARKINGS TO SHOW CHANGES MADE

DISPLAY DEVICE

BACKGROUND OF THE INVENTION

The present invention relates to a display device, and, more particularly,
5 to a display device which includes thin film transistors, each of which includes a semiconductor layer made of polysilicon.

For example, in an active matrix type liquid crystal display device, on a liquid-crystal-side surface of one ~~substrate out of~~ a pair of substrates which are arranged to face each other with liquid crystal disposed therebetween, gate
10 signal lines ~~which extend~~ in the x direction and are arranged in parallel in the y direction, and drain signal lines ~~which extend~~ in the y direction and are arranged in parallel in the x direction ~~are formed~~, and regions which are surrounded by these respective signal lines constitute pixel regions.

~~Then, each~~ Each pixel region at least includes a thin film transistor, which
15 is driven in response to scanning signals from ~~the a~~ gate signal line, and a pixel electrode to which video signals from the drain signal line are supplied through the thin film transistor. ~~Here, as the thin film transistor~~ For this purpose, a thin film transistor which uses polysilicon for forming a semiconductor layer at a low temperature has been ~~known~~ provided. With the use of such a thin film
20 transistor, high-speed switching can be performed.

Further, ~~the an~~ an enhancement of the functions and ~~the a~~ a reduction ~~of in the~~ cost can be achieved by ~~a the~~ the following constitution. That is, a peripheral drive

circuit for supplying the scanning signals to the gate signal lines, or a peripheral drive circuit for supplying the video signals to the drain signal lines, is formed on one substrate, polysilicon is used as ~~a~~the material of a semiconductor layer of each transistor which is incorporated into the peripheral drive circuit, and the

5 transistor is formed in parallel with the thin film transistor within the pixel region.

On the other hand, along with ~~the~~an increase ~~of~~in the size of a liquid crystal display device, ~~the~~there has been a demand for further reduction of the resistance of the gate signal lines~~is requested.~~ In this case, it is proper to use aluminum as ~~a~~the material of the gate signal lines. However, it has been found

10 that aluminum does not exhibit ~~the~~ sufficient heat resistance against the heat ~~of~~ produced during activated annealing of the polysilicon semiconductor layer, for example.

Accordingly, as to the construction of the gate signal line, ~~a gate signal line which uses it~~ has been suggested to use a high-melting-point metal as ~~a~~the

15 material of a lower layer and ~~stacks to~~ stack a barrier layer on the lower layer (see Japanese Unexamined Patent Publication Hei 10 (1998)-247733 (hereinafter referred to as patent literature 1)), to provide a gate signal line in which ~~forms a~~ cap layer is formed above an aluminum line and ~~forms a~~ barrier layer is formed on side faces of the aluminum line (see Japanese Unexamined

20 Patent Publication Hei11 (1999-87716 (hereinafter referred to as patent literature 2)), and to provide a gate signal line which is made of an aluminum layer and has upper and lower layers thereof covered with a high-melting-point metal (see Japanese Unexamined Patent Publication Hei6 (1994)-148683(hereinafter referred to as patent literature 3))~~and the like have been known.~~

Further, the gate signal lines are usually formed integrally with gate electrodes of the thin film transistors; and, the thin film transistors are, for purposes preventing the degradation of the characteristics thereof by obviating a any direct contact thereof with the liquid crystal, are covered with an insulation film which is referred to as a protective film, for example. Here, it is important to judge whether or not the gate signal lines are favorably covered with the insulation film or not (see Japanese Unexamined Patent Publication Hei11 (1999)-135797 (hereinafter referred to as patent literature 4)).

10 SUMMARY OF THE INVENTION

However, with respect to the liquid crystal display devices which are described in the above-mentioned respective literatures publications, since the aluminum layer is exposed from the side surfaces of the gate signal line, there has been is a drawback in that a so-called hillock is grown may grow from the aluminum layer (patent literature 4).

Further, even when an alloy element is added to prevent the generation of the hillock, there arises a drawback in that the electric resistance thereof is largely increased (patent literature 1). Further, any countermeasure to prevent the generation of the hillock in the periphery of the gate signal line, including the side surface, may give rise to a the drawback that the countermeasure has the a complicated constitution which requires the increase of in the man-hours needed for manufacturing the display device (patent literature 2).

The present invention has been made under such circumstances, and it is an advantage object of the present invention to provide a display device having

gate signal lines and gate electrodes of thin film transistors which ~~can reduce the~~
have a reduced resistance, while preventing the generation of a hillock, in spite
of the simple structure thereof.

~~To briefly explain representative inventions among~~ Representation
5 aspects of the inventions-invention disclosed in this specification, ~~they~~ are as
follows.

~~Means~~ Example 1.

The present invention is directed to, for example, a display device having
thin film transistors on a substrate thereof, wherein the display device includes
10 gate patterns, in each of which a gate line and a gate electrode of the thin film
transistor are integrally formed, ~~the~~ The gate pattern is constituted by at least
three-layered films consisting of a lowermost layer, an intermediate layer formed
of at least one layer and an uppermost layer at least at either a portion of the thin
film transistor or a portion of the gate pattern which crosses a drain line; and,
15 the end portions of the intermediate layer are ~~retracted~~ recessed from the end
portions of the uppermost layer and the end portions of the lowermost layer.

~~Means~~ Example 2.

The display device according to the present invention is, for example,
based on the constitution of ~~means~~ Example 1 and is characterized in that the
20 intermediate layer is formed of a material selected from the group consisting of
pure Al, an Al alloy, pure Ag, an Ag alloy, pure Cu and a Cu alloy; and, the
uppermost layer and the lowermost layer are formed of a metal having a melting
point that is higher than a the melting point of the material of the intermediate
layer.

~~Means-Example 3.~~

The display device according to the present invention is, for example, based on the constitution of ~~means-Example 2~~ and is characterized in that the uppermost layer and the lowermost layer are formed of pure Mo or an Mo alloy.

5 ~~Means-Example 4.~~

The display device according to the present invention is, for example, based on the constitution of ~~means-Example 2~~ and is characterized in that the uppermost layer and the lowermost layer are formed of an Mo-W alloy.

~~Means-Example 5.~~

10 The display device according to the present invention is, for example, based on the constitution of any one of ~~means-Examples 1 to 4~~ and is characterized in that end portions of the uppermost layer are ~~retracted~~spaced inwardly from end portions of the lowermost layer.

~~Means-Example 6.~~

15 The display device according to the present invention is, for example, based on the constitution of any one of ~~means-Examples 1 to 5~~ and is characterized in that the thin film transistor includes a semiconductor layer and the gate electrode is arranged above the semiconductor layer.

~~Means-Example 7.~~

20 The display device according to the present invention is, for example, based on the constitution of any one of ~~means-Examples 1 to 6~~ and is characterized in that the thin film transistor includes a polycrystalline semiconductor layer.

~~Means-Example 8.~~

The present invention is directed to, for example, a display device having thin film transistors on a substrate thereof, wherein the display device includes gate patterns, in each of which a gate line and a gate electrode of the thin film transistor are integrally formed, and an insulation film which covers the gate pattern; ~~the~~ The gate pattern is constituted by at least three-layered films consisting of a lowermost layer, an intermediate layer formed of at least one layer and an uppermost layer at least at either a portion of the thin film transistor or a portion of the gate pattern which crosses a drain line; ~~and~~. The end portions of the uppermost layer of the gate electrode are ~~retracted~~ spaced inwardly from the end portions of the lowermost layer; and, at the same time, the end portions of the intermediate layer of the gate electrode are ~~retracted~~ recessed from the end portions of the uppermost layer and the end portions of the lowermost layer. Means-Example 9.

The display device according to the present invention is, for example, based on the constitution of means-Example 8 and is characterized in that the thin film transistor includes a semiconductor layer and the gate electrode is arranged above the semiconductor layer.

Means-Example 10.

The display device according to the present invention is, for example, based on the constitution of means-Example 9 and is characterized in that the intermediate layer is formed of a material selected from the group consisting of pure Al, an Al alloy, pure Ag, an Ag alloy, pure Cu and a Cu alloy; and the uppermost layer and the lowermost layer are formed of a metal having a melting

point that is higher than ~~a~~the melting point of the material of the intermediate layer.

~~Means-Example~~ 11.

The display device according to the present invention is, for example,
5 based on the constitution of ~~means-Example~~ 10 and is characterized in that the uppermost layer and the lowermost layer are formed of pure Mo or an Mo alloy.

~~Means-Example~~ 12.

The display device according to the present invention is, for example,
based on the constitution of ~~means-Example~~ 10 and is characterized in that the
10 uppermost layer and the lowermost layer are formed of an Mo-W alloy.

~~Means-Example~~ 13.

The display device according to the present invention is, for example,
based on the constitution of ~~means-Example~~ 10 and is characterized in that the
uppermost layer and the lowermost layer are formed of an Mo alloy, and ~~an~~the
15 etching rate of the Mo alloy of the uppermost layer is faster than ~~an~~the etching rate of Mo alloy of the lowermost layer.

~~Means-Example~~ 14.

The display device according to the present invention is, for example,
based on the constitution of ~~means-Example~~ 13 and is characterized in that the
20 lowermost layer is formed of an Mo-Cr alloy and the uppermost layer is formed of an Mo-W alloy.

~~Means-Example~~ 15.

The display device according to the present invention is, for example,
based on the constitution of any one of ~~means-Examples~~ 8 to 14 and is

characterized in that the semiconductor layer includes an LDD region, and the lowermost layer of the gate electrode has at least a portion thereof that is overlapped with respect to the LCD region.

~~Means-Example 16.~~

5 The display device according to the present invention is, for example, based on the constitution of any one of ~~means-Examples 8 to 15~~ and is characterized in that the thin film transistor includes a polycrystalline semiconductor layer.

 The present invention is not limited to the above-mentioned constitutions
10 and various modifications are conceivable without departing from the technical concept of the present invention.

BRIEF DESCRIPTION OF THE DRAWINGS

 Fig. 1 is a diagrammatic plan view showing one embodiment of a pixel of
15 a display device according to the present invention;

 Fig. 2 is a cross-sectional view taken along a line II-II in Fig. 1;

 Fig. 3 is a cross-sectional view taken along a line III-III in Fig. 1;

 Fig. 4A to Fig. 4C are sectional views showing ~~essential steps of one embodiment of a manufacturing method in the manufacture~~ of a display device
20 according to an embodiment of the present invention;

 Fig. 5 is a cross-sectional view showing another embodiment of the pixel of the display device according to the present invention;

Fig. 6A to Fig. 6C are sectional views showing essential steps of one embodiment of a manufacturing method in the manufacture of a the display device shown in Fig. 5;

Fig. 7 is a cross-sectional view showing another embodiment of the pixel
5 of the display device according to the present invention;

Fig. 8 is a cross-sectional view showing another embodiment of the pixel of the display device according to the present invention;

Fig. 9A to Fig. 9C are views showing essential steps of one embodiment of the manufacturing method in the manufacture of the display device shown in
10 Fig. 8;

Fig. 10A and Fig. 10B are views showing essential steps of another embodiment of the manufacturing method in the manufacture of the display device according to the present invention; and

Fig. 11A to Fig. 11C are views showing essential steps of another
15 embodiment of the manufacturing method in the manufacture of the display device according to another embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Embodiments-Various embodiments of a display device according to the
20 present invention are will be explained in conjunction with the drawings.

<<Constitution of a pixel>>

Fig. 1 is a plan view showing the constitution of a pixel of a liquid crystal display device, for example; Fig. 2 is a cross-sectional view taken along a line II-II in Fig. 1; and Fig. 3 is a cross-sectional view taken along a line III-III in Fig. 1.

Here, a liquid crystal display part of the liquid crystal display device is configured such that a large number of pixels are arranged in a matrix array. That is, the pixel shown in Fig. 1 is one of these pixels and the pixels which are arranged at upper and lower peripheral sides and left and right peripheral sides thereof are omitted.

~~In-respective-drawing the manufacture of the display device,~~ first of all, a silicon nitride film 2 and a silicon oxide film 3 are sequentially formed over a liquid-crystal-side surface of a transparent insulation substrate 1. The silicon nitride film 2 and the silicon oxide film 3 are formed to prevent ionic impurities contained in the transparent insulation substrate 1 from affecting ~~a-the~~ thin film transistor TFT ~~described-which is to be formed~~ later.

Then, on a surface of the silicon oxide film 3, a semiconductor layer 4 formed of a polysilicon layer, for example, is formed. The semiconductor layer 4 is formed by polycrystallizing an amorphous Si film₁ which is formed by a plasma CVD device, for example, using an excimer laser.

The semiconductor layer 4 is constituted by a strip-like portion 4A₁ which is formed so as to be arranged close to and substantially parallel to a gate line layer 18, which will be described later₁ and₁ a substantially rectangular portion 4B₁ which is arranged close to the portion 4A, is formed integrally with the portion 4A and occupies a portion of the pixel region.

Here, the silicon nitride film 2, the silicon oxide film 3 and the amorphous Si film₁ before polycrystallization₁ are respectively formed by a plasma CVD method, for example. Thereafter, only the amorphous Si film is selectively

etched (for example, dry etching) using a photolithography technique to form the above-mentioned pattern₁ which is constituted by respective portions 4A and 4B.

A semiconductor layer of the strip-like portion 4A is formed as a semiconductor layer of a thin film transistor TFT, while a semiconductor layer of the substantially rectangular portion 4B is formed as one electrode of the respective electrodes of a capacitive element Cstg1 to be described later.

On the surface of the transparent insulation substrate 1 on which such semiconductor layers 4 are formed, a first insulation film 5 made of SiO₂ is formed by a CVD method, for example, ~~is formed~~ such that the first insulation film 5 also covers the semiconductor layers 4.

The first insulation film 5 functions as a gate insulation film in a region where the thin film transistor TFT is formed₁ and, at the same time, it functions as one of the dielectric films in a region where the capacitive element Cstg1 ~~described later is~~ to be formed.

Then, on an upper surface of the first insulation film 5, the gate line layers 18₁ which extend in the x direction as seen in the drawing and are arranged in parallel in the y direction as seen in the drawing₁ are formed. These gate line layers 18 define rectangular pixel regions together with drain line layers 14 to be described later.

Further, a portion of each gate line layer 18 extends into the inside of the pixel region and is overlapped with the strip-like semiconductor layer 4A in a crossing manner. The extension portion of the gate line layer 18 is formed as a gate electrode GT of the thin film transistor TFT.

Due to such a constitution, the gate line layers 18 and the gate electrodes GT are respectively and integrally formed as a gate pattern, ~~wherein and the~~ materials of these elements have the same constitution. Hereinafter, in this specification, the term "gate pattern" means the gate line layer 18 and the gate electrode GT, which are formed integrally, ~~while although~~ the gate line layers 18 and the gate electrode GT may be used individually when necessary.

Here, the gate pattern has ~~the a~~ three-layered structure, for example, wherein a lowermost layer 6 is formed of an Mo-W alloy film, an intermediate layer 7 is formed of an Al-Si alloy film, and an uppermost layer 8 is formed of an Mo-W alloy film.

~~The A reduction of in the~~ resistance is requested with respect to of the gate pattern is desirable, and, hence, as a material of the gate pattern per se, it is desirable to use an Al-Si alloy film. However, in high-temperature annealing, which is performed for activating the semiconductor layer 4 in a step after the formation of a second insulation film 12 to be described later, the Al-Si alloy film exhibits a drawback with respect to the heat resistance. Accordingly, the gate pattern has the above-mentioned three-layered structure using the Mo-W alloy film, which is made of a metal having a high melting point.

Further, with respect to the gate pattern, the intermediate layer 7 has side surfaces (end portions) ~~formed in a retracted manner that are recessed from the~~ end portions of the lowermost layer 6 and end portions of the uppermost layer 8, such that the end portions of the intermediate layer 7 are scooped spaced inwardly with respect to the lowermost layer 6 and the uppermost layer 8. An

advantageous effect obtained by such a constitution will be explained later in detail.

Then, in this embodiment, the uppermost layer 8 of the gate pattern is formed such that the end portions thereof are ~~retracted~~ spaced inwardly from the end portions of the lowermost layer 6. An advantageous ~~effects~~ effect obtained by such a constitution ~~are also~~ will be explained later in detail.

In other words, the respective layers of the gate pattern have ~~the~~ their center axes in the extending direction substantially aligned with each other, ~~and~~ while the widths (widths in the direction which crosses the extension direction) are formed so as to be increased in the order of the intermediate layer 7, the uppermost layer 8 and the lowermost layer 6.

After the formation of the gate line layer 18, the ion implantation of impurities is performed by way of the first insulation film 5₁ and, hence, a region of the semiconductor layer 4₁ except for a ~~the~~ portion immediately below the gate electrodes GT₁ is made conductive, whereby a source region 10S and a drain region 10D of the thin film transistor TFT are formed; and, at the same time, one electrode ~~out of the~~ respective electrodes of the capacitive elements ~~element~~ Cstg1 is formed.

On the other hand, to make the semiconductor layer 4B conductive, only the region of the semiconductor layer 4B may be doped with impurities of high concentration in advance, and, thereafter, a capacitive signal line 19 may be formed.

Further, in the above-mentioned semiconductor layer 4B, between the region (the channel region) ~~right~~ immediately below the gate. electrode GT and

the drain region 10D₁ as well as between the channel region and the source region 10S, LDD layers 11 that are doped with impurities of low concentration are respectively formed. The LDD layers 11 are provided for alleviating the concentration of an electric field which is generated between the drain region
5 100 or the source region 10S and the gate electrode GT.

Further, in the region close to the semiconductor layer 4A within the pixel region and on the upper surface of the first insulation film 5, the capacitive signal line 19₁ extending in the x direction as seen in the drawing₁ is integrally formed with a capacitive electrode 20₁ which has a large width. The capacitive signal line
10 19 and the capacitive electrode 20 are simultaneously formed with the gate line layer 18, for example. Accordingly, the capacitive signal line 19 and the capacitive electrode 20 are formed on the same layer as the gate line layer 18₁ and they are formed of the same material as the gate line layer 18. Further, the capacitive signal line 19 and the capacitive electrode 20 have the same cross-
15 sectional structure as the gate line layer 18.

In this case, the capacitive electrode 20 is formed such that the capacitive electrode 20 is overlapped with the semiconductor layer 4B₁ and₁ hence, one capacitive element Cstg1₁ which uses the semiconductor layer 4B as another electrode (connected to the source region 10S of the thin film transistor TFT) and
20 the first insulation film 5 as a dielectric film₁ is formed. Here, the reason ~~that~~ why one capacitive element Cstg1 is provided lies in the fact that, as will be explained later, another capacitive element Cstg2 is overlapped with the capacitive element Cstg1₁ and these capacitive elements are connected in parallel so as to increase the capacitive value.

Then, a second insulation film 12₁ which is made of SiO₂, for example, is formed over the upper surface of the first insulation film 5₁ such that the second insulation film 12 also covers the gate wiring layers 18 and the capacitive signal lines 19 (capacitive electrodes 20) . The second insulation film 12 is formed by a
5 CVD method, for example.

In this case, any one of the gate line layer 18, the gate electrode GT and the capacitive signal line 19 has ~~the~~ a three-layered structure, wherein each layer has a substantially trapezoidal shape with ~~a~~ the width thereof increased in the ascending order of the intermediate layer 7, the uppermost layer 8 and the
10 lowermost layer 6. Accordingly, it is possible to obtain an advantageous effect in that ~~a~~ the so-called coverage by the second insulation film 12 is enhanced. Further, the intermediate layer 7 of any one of the gate line layer 18, the gate electrode GT and the capacitive signal line 19 is formed such that the intermediate layer 7 is ~~retracted~~ recessed from the uppermost layer 8 and the
15 lowermost layer 6₁ and the second insulation layer 12 intrudes into these ~~retracted portions~~ recesses whereby ~~the~~ complete coverage can be surely ~~performed~~ achieved.

Then, after the formation of the second insulation film 12, a step in which so-called annealing is performed at a temperature of approximately 400°C so as
20 to activate the implanted dopant in the semiconductor layer 4 is executed. In this case, as the intermediate layer 7 of any one of the gate line layer 18, the gate electrode GT and the capacitive signal line 19, an Al-Si alloy film is used.

Although there exists no problem with respect to the front and back surfaces of the intermediate layer 7, that is, portions which are brought into

contact with the uppermost layer 8 and the lowermost layer 6 made of an Mo-W alloy film, it is impossible to avoid the generation of a so-called hillock on side wall surfaces of the intermediate layer 7. The hillock ~~means~~ is represented by a large number of needle-like conductive materials which grow from an Al material.

5 The higher the temperature at the time of annealing, the greater the growth of the hillock is accelerated; and, hence, there arises a problem in that the hillock is may become electrically connected with ~~other~~ another conductive layer (for example, the drain line layer 14 or a source electrode described later) which is arranged close to the hillock.

10 However, in this embodiment, as described above, the intermediate layer 7 is configured such that the side wall surfaces thereof are properly ~~retracted~~ recessed from the side wall surfaces of the uppermost layer 8 and the lowermost layer 6, and, hence, even when ~~the~~ a hillock grows on the side wall surfaces, the growth of the hillock can be suppressed by an amount corresponding to the

15 ~~retraction of~~ extent to which the side wall surfaces are recessed. In other words, this embodiment has an advantageous effect in that a ~~drawback~~ possible problem attributed to the growth of a hillock can be sufficiently reduced.

Then, on an upper surface of the second insulation layer 12, the drain line layers 14, which extend in the y direction as seen in the drawing and are

20 arranged in parallel in the x direction as seen in the drawing, are formed. These drain line layers 14 define the pixel regions together with the above-mentioned gate line layers 18.

The drain line layer 14 has a portion thereof connected to a drain region 10D (a side which is connected with the drain line layer 14 is referred to as the

drain region in this specification) of the thin film transistor TFT via a contact hole CH2, which is formed in the second insulation film 12 and the first insulation film 5.

Further, source electrodes 22 are formed simultaneously with the formation of the drain line layers 14, wherein the source electrode 22 is formed over an upper surface of the source region 10S of the thin film transistor TFT and slightly extends toward the pixel region from the upper surface. The source electrode 22 is also connected to the source region 10S of the thin film transistor TFT via a contact hole CH3 which is formed in the second insulation film 12 and the first insulation film 5.

Then, a third insulation film 15A and a fourth insulation film 15B are sequentially formed over the upper surface of the second insulation film 12, such that the third insulation film 15A and the fourth insulation film 15B also cover the drain line layers 14 and the source electrodes 22. The third insulation film 15A is formed of SiO₂ or SiN, for example, and the fourth insulation film 15B is formed of an organic material film, such as a resin, for example.

~~These~~ The third insulation film 15A and fourth insulation film 15B function as protective films for obviating ~~the~~ any direct contact of the thin film transistors TFT with the liquid crystal. By forming the fourth insulation film 15B using the organic material film and by relatively increasing ~~a~~ the film thickness of the fourth insulation film 15B, it is possible to flatten ~~a~~ the surface of the fourth insulation film 15B, whereby it is possible to obtain advantageous effects in that the orientation of the liquid crystal can assume a favorable state, and, at the same time, the dielectric constant of the protective film as a whole can be reduced.

On an upper surface of the fourth insulation film 15B, pixel electrodes 17, that are made of a light transmitting material, such as an ITO (Indium-Tin-Oxide) film, for example, are formed, and the pixel electrode 17 is formed over the whole area of the pixel region. Since the protective film is configured to have ~~the~~
5 a small dielectric constant, as described above, the protective film is formed to ~~make a cause the~~ periphery thereof ~~overlapped to overlap~~ with the drain line layers 14 and the gate line layers 18, and, hence, the so-called numerical aperture of the pixels can be enhanced.

Here, the material of the pixel electrode 17 is not limited to the above-
10 mentioned ITO film, and it is needless to say that the pixel electrode 17 may be formed of a light transmitting material, such as ITZO (Indium-Tin-Zinc-Oxide), IZO (Indium-Zinc-Oxide), SnO_2 (Tin-Oxide), In_2O_3 (Indium-Oxide) or the like.

The pixel electrode 17 has a portion thereof which is arranged close to the thin film transistor TFT that is connected to the source electrode 22 via a contact
15 hole CH4, which is formed in the fourth insulation film 15B and the third insulation film 15A. Here, the pixel electrode 17 forms a capacitive element Cstg2 which uses the fourth insulation film 15B and the third insulation film 15A as dielectric films between the pixel electrode 17 and the capacitive electrode 20, wherein the capacitive element Cstg2 is configured to be arranged in parallel
20 ~~to with~~ the above-mentioned capacitive element Cstg1.

With respect to ~~the a~~ pixel having such a constitution, when the scanning signal is supplied to the gate line layer 18, the thin film transistor TFT is turned on and the video signal from the drain line layer 14, which is supplied at the timing of supply of the scanning signal, is supplied to the pixel electrode 17

through the thin film transistor TFT. ~~Then~~ Thus, ~~the a~~ video signal supplied to the pixel electrode 17 is stored in the pixel electrode 17 for a relatively long time due to the capacitive elements Cstg (Cstg1, Cstg2).

Although Al-Si is used as the material of the intermediate layer 7 in this
5 embodiment, ~~the a~~ similar drawback arises in cases of use of a material such as pure Al, Al-Cu, Al-Cu-Si or the like. Accordingly, it is needless to say that these materials also can be ~~also~~ used as the material of the intermediate layer 7.

Further, there may be a case ~~that in which~~ an ionic material flows out from the intermediate layer 7 of the gate electrode at the time of forming the insulation
10 film 12, for example, and the ionic material reaches the surface of the insulation film 5₁ thus contaminating the insulation film 5₁ whereby the characteristics of the thin film transistor TFT ~~is~~ are degraded.

Further, there may arise a case in which₁ during ~~a the~~ step for of forming the insulation film 12, the above-mentioned ionic material flows out to the surface
15 of the insulation film 12 from the intermediate layer 7 of the gate electrode₁ and this out-flow continues until the completion of the insulation film 12₁ and a leak leakage current is generated between the drain electrode or the source electrode which is formed thereafter and the gate electrode through the above-mentioned ionic material.

20 Accordingly, in this embodiment, by adopting ~~the a~~ constitution in which the intermediate layer 7 of the gate electrode is ~~retracted~~ recessed from the other ~~layer~~ layers₁ such as the lowermost layer 6 or the uppermost layer 8, the above-mentioned contamination path can be ~~eventually elongated~~₁ whereby the occurrence of the above-mentioned drawback can be suppressed.

In view of the above, the material of the intermediate layer 7 of the gate electrode is not limited to the a material which is liable to easily generate the a hillock₁ and it is needless to say that any material which is liable to generate produce contamination which generates the ~~leak~~ a leakage current₁ as described above₁ can be used as the material of the intermediate layer 7. That is, a material such as Al-Nd, Al-Y, Al-Hf-Y can be used as the material of the intermediate layer 7. It is needless to say that this selection of the material of the intermediate layer 7 is also applicable to the embodiments to be described hereinafter.

<<Manufacturing method>>

Fig. 4A to Fig. 4C are sectional views showing ~~essential~~ sequential steps of ~~one embodiment of in~~ the manufacturing method used for fabrication of the pixel shown in Fig. 1 to Fig. 3. Here, the background films (the silicon nitride film 2 and the silicon oxide film 3) are omitted from the drawing.

First of all, in Fig. 4A, a photoresist film 9 is left in the region where a gate pattern is formed. Using the photoresist film 9 as a mask, an Mo-W alloy film constituting the uppermost layer 8, an Al-Si alloy film constituting the intermediate layer 7 below the uppermost layer 8 and an Mo-W alloy film constituting the lowermost layer 6 below the intermediate layer 7₁ which are exposed from the mask₁ are sequentially etched.

In this case, a phosphoric acid system etchant is used as an etchant₁ and the uppermost layer 8, the intermediate layer 7 and the lowermost layer 6 are respectively collectively etched using such an etchant. Then, by applying a so-

called isotropic etching, side etching of approximately $0.3\mu\text{m}$ to $1.0\mu\text{m}$ is performed with respect to the photoresist film 9.

In this case, ~~the a~~ film composition and ~~the an~~ etchant which slightly accelerates the side etching of the intermediate layer 7 with respect to the lowermost layer 6 and the uppermost layer 8 are adopted. Alternately, after performing the collective etching, the intermediate layer 7 may be selectively subjected to side etching with respect to the lowermost layer 6 and the uppermost layer 8.

Due to such steps, the center axes in the extending direction of the respective layers of the gate pattern are substantially aligned, while the widths (the widths in the direction which crosses the extending direction) of respective layers are set such that the widths are increased in the ascending order of the intermediate layer 7, the uppermost layer 8 and the lowermost layer 6.

Further, to make the respective layers of the gate pattern have ~~the a~~ similar cross-sectional structure, a material such as Ti or TiN is used as the material of the uppermost layer 8 and the lowermost layer 6, and the three layers may be collectively etched by dry etching. This is because, ~~that~~ when a chloride system gas is used in dry etching, ~~a the~~ dry etching rate of Al becomes faster than ~~a the~~ dry etching rate of Ti.

Then, after forming the gate pattern in this manner, using the above-mentioned photoresist film 9 as a mask, phosphorous (P) is implanted to form n^+ ~~impurities-impurity~~ regions in the semiconductor layer 4A, thus forming the drain region 10D and the source region 10S.

Then, as shown in Fig. 4B, the photoresist film 9 is removed and n⁻ impurities are doped using the gate pattern as a mask whereby ~~the~~LDD (Lightly Doped Drain) structures (LDD layers 11) are formed in ~~the~~a self-alignment manner between the drain region 10D and the source region 10S of the semiconductor layer 4A and the gate pattern.

Further, as shown in Fig. 4C, the second insulation film 12 is formed over the upper surface of the first insulation film 5₁ such that the second insulation film 12 also covers the gate patterns₁; the contact holes CH2 and CH3 are formed in the second insulation film 12₁; and₁ the drain line layers 14 (drain electrodes) and the source electrodes 22 are formed on the second insulation film 12.

The second insulation film 12 is formed such that an SiO₂ film, for example, is formed by a CVD method, for example. After forming the second insulation film 12, annealing is performed at a temperature of approximately 400 ~~degree~~ degrees centigrade for activating the dopant implanted into the semiconductor layer 4A.

Here, due to the heat generated at the time of forming the second insulation film 12 and at the time of annealing, ~~the~~a hillock ~~grows~~may grow from the intermediate layer 7 of the gate pattern. In this case, since the intermediate layer 7 is configured to be sandwiched between the lowermost layer 6 and the uppermost layer 8, the growth of ~~the~~a hillock is suppressed on ~~a~~the contact surface between the intermediate layer 7 and the lowermost layer 6₁ as well as on a contact surface between the intermediate layer 7 and the uppermost layer 8₁ by the lowermost layer 6 and the uppermost layer 8. However, ~~the~~a mutual dispersion is observed between the intermediate layer 7 and the lowermost layer

6₁ or between the intermediate layer 7 and the uppermost layer 8₁ at the time of heating₁ and there may be a case in which the infiltration of the hillock or Al is generated beyond the lowermost layer 6 or the uppermost layer 8 due to such diffusion. Accordingly, it is appropriate to set the film thicknesses of the
5 lowermost layer 6 and the uppermost layer 8 to approximately 20nm (when annealing is performed at a temperature of approximately 400 degree degrees centigrade) or more.

Further, although the side wall surfaces of the intermediate layer 7 are not covered with ~~either~~ another metal layer, the side wall surfaces of the intermediate
10 layer 7 are configured to be ~~retracted~~ recessed with respect to the side wall surfaces of the lowermost layer 6 and the uppermost layer 8. Accordingly, even when a slight amount of hillock is generated in the lateral direction, it is possible to avoid the generation of ~~the~~ a hillock which extends upwardly and downwardly beyond the lowermost layer 6 and the uppermost layer 8.

15 The contact holes CH2 and CH3 which are formed in the second insulation film 12 and the first insulation film 5 are formed by continuous etching using a buffered hydrofluoric acid.

The drain line layer 14 (drain electrode) and the source electrode 22 have, for example, ~~the~~ a three-layered structure formed of Ti/Al-Si/Ti, for
20 example, and they are formed such that₁ after forming a resist pattern, the collective etching is performed by dry etching which uses a chlorine gas. In this case, it is needless to say that, as the material of the drain line layer 14 (drain electrode) and the source electrode 22, ~~the~~ a three-layered structure formed of

MoW/Al-Si/MoW is adopted in the same manner as the gate line layer 18, wherein the three-layered structure is processed by wet etching.

Although not shown in Fig. 4A to Fig. 4C, in steps which follow the step shown in Fig. 4C, the third insulation film 15A is formed using SiN, for example, by a CVD method. Thereafter, the third insulation film 15A is subjected to hydrogen annealing in a hydrogen atmosphere at a temperature of 400 degree degrees centigrade. Also, in this case, due to the constitution of the present invention, there arises no drawback attributed to the formation of a hillock of on the intermediate layer 7 in the gate pattern during annealing.

Then, the fourth insulation film 15B is formed by applying a photosensitive acrylic resin and, thereafter, by performing the exposure and development of the photosensitive acrylic resin. Then, the contact hole CH4 is formed in the fourth insulation film 15B. Thereafter, the scum of the photosensitive acrylic resin is removed by oxygen ashing.

Thereafter, the ITO film is formed and the pixel electrode 17 is formed by performing the selective etching using a photolithography technique. As etching applicable to this case, wet etching which uses oxalic acid, aqua regia or hydrobromic acid, for example, is adopted.

Embodiment 2.

Fig. 5 is a cross-sectional view showing another embodiment of the display device according to the present invention, ~~and corresponds~~ it is similar to Fig. 2.

The constitution which makes this embodiment different from the constitution shown in Fig. 2 lies in, the fact that, while the thin film transistor TFT

shown in Fig. 2 is an n-channel type MIS transistor (Metal Insulator Semiconductor), Fig. 5 shows a p-channel type MIS transistor.

With respect to the p-channel type MIS transistor, in a scanning signal drive circuit which supplies scanning signals to gate line layers 18, or a video signal drive circuit which supplies video signals to the drain line layers 14, a complementary type transistor is formed together with the n-channel type MIS transistor, thus constituting a CMOS (or CMIS) type transistor.

Unlike the n-channel type MIS transistor, the any degradation of the characteristics attributed to an electric field at the drain end portions in the p-channel type MIS transistor has a relatively small significance, and, hence, the necessity to adopt the LDD structures shown in Fig. 2 is small; and therefore, it is sufficient to form p^+ regions which constitute the source region 10S and the drain region 10D at both ends of the channel layer ~~right~~ immediately below the gate electrode GT_1^{**} as shown in Fig. 5.

Also, in this case, the gate electrode GT and the gate line layer 18 have a three-layered structure, for example, wherein the center axes in the extending direction of the respective layers are substantially aligned with each other and their widths (widths in the direction which crosses the extending direction) are formed such that the widths are increased in the ascending order of the intermediate layer 7, the uppermost layer 8 and the lowermost layer 6.

Fig. 6A to Fig. 6C are views showing sequential steps of ~~one embodiment~~ of the manufacturing method used in the fabrication of the above-mentioned display device, and ~~correspond~~ it is similar to Fig. 4A to Fig. 4C. This embodiment differs from the embodiment shown in Fig. 4A to Fig. 4C with

respect to points that the photoresist film 9_i which is provided for forming the gate pattern_i is removed after the formation of the gate pattern_i and p⁺ impurities made of boron (B), for example, are implanted using the gate pattern as a mask.

Here, when the p-channel type MIS transistor is formed in parallel to the
5 n-channel type MIS transistor to form the CMOS constitution, the source region 10S, the drain region 10D and the LDD structure of the n-channel type MIS transistor are formed_i and, thereafter, at least the n-channel type MIS transistor is covered with ~~the~~ a mask, a photoresist film having an opening is formed over a portion where the p-channel type MIS transistor is formed, and p⁺ impurities are
10 counter-doped.

Further, after the formation of the second insulation film 12, annealing is collectively performed for activating the p-channel type MIS transistor and the n-channel type MIS transistor.

Embodiment 3.

15 Fig. 7 is a sectional view for explaining showing another embodiment of the display device according to the present invention_i and ~~corresponds it is~~ similar to Fig. 2. The constitution which makes this embodiment different from the embodiment shown in Fig. 2 lies in the structure of the gate electrode GT of the thin film transistor TFT.

20 The gate electrode GT has ~~the~~ a three-layered structure formed of respective layers made of Ti, Al-Si, Ti_i ~~respectively~~ which correspond to layers starting from the lowermost layer 6 to the uppermost layer 8. In this case, Ti which is the material of the lowermost layer 6 and the uppermost layer 8 is a metal having a high melting point similar to the Mo-W ~~shown~~ used in the

embodiment of Fig. 2, and the growth of a hillock ~~which grows at contact~~ surfaces between the Al-Si of the intermediate layer 7 and the Ti can be avoided due to the presence of the Ti.

Further, while the side wall surfaces of the intermediate layer 7 made of Al-Si are ~~retracted~~ recessed from the side wall surfaces of the uppermost layer 8 and the lowermost layer 6, the uppermost layer 8 and the lowermost layer 6 have ~~the~~ substantially the same width (width in the direction orthogonal to the extending direction).

With the use of Ti as the ~~materials~~ material of the lowermost layer 6 and the uppermost layer 8 of the gate electrode GT, ~~a~~ the cross-sectional shape shown in the drawing is formed by reactive ion etching (RIE) which enables ~~the~~ an anisotropic etching. This is because ~~a~~ a the dry etching rate of Ti is faster than ~~a~~ a the dry etching rate of Al.

Embodiment 4.

Fig. 8 is a sectional view ~~for explaining~~ showing another embodiment of the display device according to the present invention, ~~and corresponds~~ it is similar to Fig. 2. The constitution which makes this embodiment different from the embodiment shown in Fig. 2 lies in the fact that ~~the~~ a so-called COLD (Gate Overlapped LDD) structure is adopted.

That is, with respect to the semiconductor layer 4A, structurally, a channel layer is formed at the center region thereof, LDD layers 11 are formed outside the channel layer, and source regions 10S and the drain region 10D are formed outside the LDD layers 11. In such a structure, the LDD layers 11 are formed such that the LDD layers 11 are overlapped ~~with~~ by the gate electrode GT.

Further, in this embodiment, the channel layer is formed such that the channel layer ~~is overlapped~~ overlaps with a material layer which constitutes the uppermost layer 8 of the gate electrode GT, while the LDD layers 11 are formed such that the LDD layers 11 are overlapped ~~with~~ by a material layer which

5 constitutes the lowermost layer 6, formed in a projected manner from the material layer which constitutes the uppermost layer 8 of the gate electrode GT. Accordingly, both of the source region 10S and the drain region 10D are formed in the a direction extending outwardly from end portions of the material layer which constitutes the lowermost layer 6 of the gate electrode GT.

10 In the thin film transistor TFT having such a constitution, by extending the gate electrode GT above the LDD layers 11 of the semiconductor layer 4A, ~~an~~ the amount of the series resistance corresponding to the LDD regions can be reduced, and, hence, ~~an~~ the ON current can be increased.

Fig. 9A to Fig. 9C are sectional views showing ~~one embodiment~~

15 sequential steps of the manufacturing method used in the fabrication of the above-mentioned display device, and ~~correspond~~ they are similar to Fig. 4A to Fig. 4C. The constitution which makes this embodiment different from the embodiment shown in Fig. 4A to Fig. 4C lies in the fact that ~~a~~ the film thickness of the lowermost layer 6 of the gate pattern, which is constituted by a sequential

20 laminated body of Mo-W, Al-Si, Mo-W, is made relatively small and is set to approximately 20nm, for example.

Then, using the photoresist film 9 at the time of forming the gate pattern as a mask, n^+ impurities are implanted, and, thereafter, the photoresist film 9 is removed. Thereafter, n^- impurities are implanted using the gate pattern as a

mask. In this case, the n⁻ impurities are doped into the inside of the semiconductor layer 4A after passing through the lowermost layer 6 of the gate pattern, and the LDD layers 11 are formed.

Embodiment 5.

5 Fig. 10A and Fig. 10B are sectional views showing another embodiment of the manufacturing method of the display device according to the present invention and ~~correspond~~ similar to Fig. 9A and Fig. 9B.

 The constitution which makes this embodiment different from the embodiment shown in Fig. 9A and Fig. 9B lies in the fact that the gate electrode
10 GT having ~~the~~ a three-layered structure uses Mo-Cr as the material of the lowermost layer 6 thereof, Al-Si as the material of the intermediate layer 7 thereof, and Mo-W as the material of the uppermost layer 8 thereof, for example.

 Then, ~~an~~ the alloy ratio of the Mo-Cr of the lowermost layer 6 is set such that ~~an~~ the etching rate thereof becomes approximately one tenth of ~~an~~ the
15 etching rate of the Mo-W of the uppermost layer 8. For example, the lowermost layer 6 is made of Mo-2.5wt%Cr and has a film thickness of 20nm at the time of forming the film, for example, and the uppermost layer 8 is made of Mo-20wt%W and has a film thickness of 50nm, for example.

 In performing ~~the~~ wet etching using the photoresist film 9, for example, the
20 etching is performed such that the side etching widths of the intermediate layer 7 and the uppermost layer 8 become approximately 1μm during etching of the lowermost layer 6 of the gate pattern. The Side-side etching amounts of the intermediate layer 7 and the uppermost layer 8 directly correspond to the width of the LCD layers.

This implies that, by changing the etching rate at the time of forming the gate pattern by ten times or around ten times, it is possible to control not only the width of the LDD layers, but also ~~an~~ the overlapped width of the LDD layer with respect to the gate electrode GT. Accordingly, it is possible to obtain an

5 advantageous effect in that both ~~of an~~ the ON current and ~~an~~ the OFF current of the thin film transistor TFT can be changed based on this control.

Here, as mentioned above, by adopting ~~the~~ wet etching in the formation of the gate pattern, ~~the~~ damage can be eliminated and ~~the~~ favorable transistor characteristics can be obtained.

10 Embodiment 6.

Fig. 11A to Fig. 11C are sectional views showing another embodiment of the display device according to the present invention, ~~and correspond~~ they are similar to Fig. 4A and Fig. 4B. The constitution which makes this embodiment different from the embodiment shown in Fig. 4A and Fig. 4B lies in the fact that

15 the gate pattern having the three-layered structure uses Mo-W as the material of the lowermost layer 6 thereof, Al-Si as the material of the intermediate layer 7 thereof, and Mo-W as the material of the uppermost layer 8 thereof; and, at the same time, for example, these respective layers are subjected to ~~the~~ collective wet etching using a phosphorous-system etchant, for example, and, thereafter,

20 ~~the~~ light etching is performed using a dilute hydrofluoric acid.

In the gate pattern formed in this manner, the width of the uppermost layer 8 is set to be smaller than the width of the lowermost layer 6, and the width of the intermediate layer 7 is set such that the width changes substantially linearly in the direction from the uppermost layer 8 to the lowermost layer 6

within a range from a width smaller than the width of the uppermost layer 8 to a width smaller than a width of the lowermost layer 6. In other words, the intermediate layer 7 has side wall surfaces thereof that are formed in a so-called normal tapered shape, such that the surface which is brought into contact with the uppermost layer 8 is ~~retracted~~ spaced inwardly from the uppermost layer 8, and the surface which is brought into contact with the lowermost layer 6 is ~~retracted~~ spaced inwardly from the lowermost layer 6.

That is, as shown in Fig. 11A, when the wet etching is collectively performed with respect to the gate pattern using the photoresist film 9 and, at the same time, ~~using the~~ a phosphorus-system etchant, for example, ~~is used,~~ by adopting employing the same material having the same etching rate ~~with respect to~~ for the lowermost layer 6 and the uppermost layer 8, the etching of the uppermost layer 8 is performed first, and, hence, the cross section of the gate pattern consisting of the uppermost layer 8, the intermediate layer 7 and the lowermost layer 6 is formed in ~~the~~ a normal tapered shape.

Then, with the use of the photoresist film 9, the drain region 10D and the source region 10S are formed by implanting the n^+ impurities.

Further, as shown in Fig. 11B, the LDD layer 11 is formed by implanting n^- impurities after removing the photoresist film 9.

Thereafter, as shown in Fig. 11C, ~~the~~ a so-called light etching of the gate pattern is performed by cleaning the gate pattern using a dilute hydrofluoric acid of 1:99. Accordingly, the intermediate layer 7 is selectively etched with respect to the uppermost layer 8 and the lowermost layer 6 so as to ~~retract~~ recess the side wall surfaces of the intermediate layer 7.

In this case, based on the time required for the cleaning, ~~a retracting the~~ amount of recessing of the sidewall surfaces of the intermediate layer 7 can be controlled. when hydrofluoric aqueous solution of 0.5%, for example, is used, it is possible to obtain ~~the retracting amount~~ a recess of the approximately 0.2 μ m.

5 Further, due to such a cleaning operation, it is also possible to obtain an advantageous effect in that the impurities that have adhered to the surface of the substrate by implantation performed in the preceding step can be removed. Additionally, it is possible to obtain an advantageous effect in that the cleaning operation after the formation of various types of insulation films can be omitted.

10 The above-mentioned respective embodiments may be used in a single form or in combination. This is because the advantageous effects of respective embodiments can be obtained in a single form or synergistically.

Further, although ~~the~~ an example has been given in which pure Al or ~~the~~ an Al alloy is used as the material of the intermediate layer 7 of the gate pattern
15 ~~is explained in~~ the description of the above-mentioned respective embodiments, pure Ag, an Ag alloy, pure Cu or a Cu alloy may be used in place of pure Al or the Al alloy. The uppermost layer 8 and the lowermost layer 6 may be made of a metal having a melting point higher than ~~a~~ the melting point of the material of the intermediate layer 7. The intermediate layer 7 may be formed of two layers or
20 more.

Further, the above-mentioned respective embodiments adopt ~~the~~ a structure in which the intermediate layer 7 is ~~retracted~~ from the lowermost layer 6 and the uppermost layer 8 in all side surfaces of the gate pattern. However, it is sufficient that such a structure is applied to either one of the portion (gate

electrode GT) of the thin film transistor or the portion which crosses the drain line (portion of the gate pattern where the gate line layer 18 crosses the drain line layer 14) in the gate pattern. This is because the drawback caused by the generation of a hillock from the intermediate layer 7 or ~~the~~ from contamination becomes apparent in such portions.

Further, in connection with the above-mentioned respective embodiments, ~~the explanation is reference has been made with respect to a~~ the liquid crystal display device. However, it is needless to say that the present invention is applicable to any display device which includes thin film transistors, such as an organic EL (Electro Luminescence) display device or the like, for example. This is because the organic EL display device also includes a pixel electrode and a counter electrode which sandwich an organic light emitting layer therebetween on each pixel formed on a surface of a substrate, and it also includes thin film transistors which are driven in response to scanning signals from gate line layers and supply video signals from drain signal lines to the pixel electrodes.

As can be clearly understood from the foregoing explanation, according to the display device of the present invention, it is possible to provide ~~the~~ a display device ~~provided with the~~ having gate signal lines and ~~the~~ gate electrodes of the thin film transistors which ~~can~~ are constructed to prevent the generation of a hillock and ~~can reduce in which~~ the resistance is reduced in spite of the simple structure.